

Magnetic fluctuations in frustrated Laves hydrides $R(\text{Mn}_{1-x}\text{Al}_x)_2\text{H}_y$

P. Cadavez-Peres¹, I. Mirebeau¹, R. Kahn¹, I.N. Goncharenko^{1,3}, E. Vincent², and O.L. Makarova³

1- Laboratoire Léon Brillouin, CEA-CNRS, CE Saclay, 91191 Gif sur Yvette, France

2- Service de Physique de l'Etat Condensé, CE Saclay, Orme des Merisiers, 91191 Gif sur Yvette, France

3- Russian Research Center 'Kurchatov Institute', 123182 Moscow, Russia

(February 6, 2008, submitted to Phys. Rev. B.)

By neutron scattering, we have studied the spin correlations and spin fluctuations in frustrated Laves hydrides, where magnetic disorder sets in the topologically frustrated Mn lattice. Below the transition towards short range magnetic order, static spin clusters coexist with fluctuating and almost uncorrelated spins. The magnetic response shows a complex lineshape, connected with the presence of the magnetic inhomogeneities. Its analysis shows the existence of two different processes, relaxation and local excitations, for the spin fluctuations below the transition.

I. INTRODUCTION

There is now a growing interest in studying magnetic fluctuations in the paramagnetic phase of strongly correlated electron systems. An original behavior in the dynamical susceptibility, where the magnetization density does not follow the single exponential decay predicted by Landau-Fermi theory is often observed. In itinerant magnets, non Fermi-liquid behavior is often associated with temperature anomalies of the thermodynamical properties, like specific heat and resistivity. In Heavy-Fermions and superconductors, it could be the precursor a quantum phase transition around zero temperature¹.

In paramagnets with localized spins, a non Fermi liquid behavior of the dynamical susceptibility could be also expected due to strong magnetic disorder, since magnetic inhomogeneities associated with disorder and frustration yield a distribution of relaxation times. However, in usual spin glasses with localized spins, although such distribution indeed exists, the excitation spectrum in the paramagnetic phase usually remains much narrower than in itinerant magnets, yielding typical energies of the fluctuating spins below 1 meV.

The intermetallic Laves compounds RMn_2 have two main characteristics²⁻⁴: i) they are at the frontier between localized and itinerant magnetism, the instability of the Mn spins being governed by the distance between first neighbor Mn pairs, and ii) they show a topological frustration of the pyrochlore Mn lattice for antiferromagnetic first neighbor Mn-Mn interactions. When R is a magnetic rare earth, the diamond-like R lattice interacts with the frustrated Mn lattice. Varying Mn-Mn interatomic distance d allows one to encompass the critical distance d_0 between localized and itinerant Mn magnetism. For $d > d_0$, spontaneous Mn moments are present and the frustrated Mn-Mn interactions dominate, whereas for $d < d_0$ Mn moments are induced by rare earth moments and the topological frustration is suppressed. Changing interatomic distances is realized by chemical substitution²⁻⁴ or by applying pressure⁵.

Introducing hydrogen in interstitial sites also modifies the magnetic properties⁶. In Laves compounds, hydrogen

expands the lattice, favoring the localization of the Mn moments, but also modifies the frustration by making Mn-Mn interactions nonequivalent. Therefore, ordered H atoms release the topological frustration, yielding long range ordered magnetic structures⁷⁻¹⁰. On the other hand, H disorder induces a random variation of the exchange interactions and therefore magnetic disorder^{11,12}.

In $\text{Y}(\text{Mn}_{1-x}\text{Al}_x)_2\text{H}_y$ and $\text{Y}(\text{Mn}_{1-x}\text{Fe}_x)_2\text{H}_y$, we studied such phases by magnetic neutron diffraction^{11,12}. Surprisingly, and in contrast with usual spin glasses, we found that these disordered magnetic phases combine short spin correlation lengths (around 10-20 Å) with high transition temperatures (100-250 K), in the same range as in the ordered parent compound. The behavior of the short range order parameter was intermediate between that expected for a canonical Edwards-Anderson spin glass, and the Brillouin curve for a non frustrated magnet.

Up to now the study of the spin fluctuations and magnetic transition in such topologically disordered phases has received little attention. A previous study of $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2$ single crystal by inelastic neutron scattering¹³, where interatomic Mn distances are close to the instability threshold, revealed very interesting features with regards to canonical spin glasses. Namely, it pointed out the existence of a large energy range of the magnetic fluctuations (up to about 40 meV), well above the typical fluctuation energy in spin glasses, and close to that observed in other itinerant magnets^{14,15}. This large energy range was attributed to the influence of both topological frustration and itinerant character of the Mn moments, without any way to clear up their respective roles.

Studying the magnetic excitations yields precious information about the microscopic nature of the magnetic ground state and ordering transition. Especially, it could help to explain why the transition temperature remains high in spite of the strong disorder. Inelastic neutron scattering is the most straightforward way to probe such excitations. We have studied the spin fluctuations in $\text{R}(\text{Mn}_{1-x}\text{Al}_x)_2\text{H}_y$ compounds ($\text{R} = \text{Y}$ or Tb) by time of flight neutron scattering, together the steady-state cor-

relations by neutron diffraction, and the low field susceptibility by static magnetization measurements. In all compounds, H disorder was achieved by substituting a small amount of Al on the Mn sites. By choosing appropriate compounds, we checked the influence of magnetic moments on the R sites, hydrogen concentration and hydrogen disorder. The results suggest an original picture of a ‘cluster glass’ magnetic state.

II. SAMPLE DESCRIPTION

Powdered samples of $R(\text{Mn}_{1-x}\text{Al}_x)_2\text{D}_y$, with ($R = \text{Y}, \text{Tb}$), Al content $x=0.09$, and different deuterium contents were prepared using the technique described in Ref. 11, and characterized by X-ray diffraction. All samples showed a single chemical phase, besides a very small amount of RH_3 impurity phase in some cases. We mostly studied three disordered samples, $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_y$, ($y=1$ and $y=4$), and $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_y$ ($y=4$). Exact D contents are given in Table I. In most cases, the deuterium isotope was chosen instead of hydrogen to decrease the incoherent background. The small Al content induces hydrogen disorder and breaks down the long range magnetic order¹¹. The Tb ion with high magnetic moment yields a strong enhancement of the magnetic fluctuations (by about a factor 10), yielding an excellent precision on the lineshape of the dynamical susceptibility. The influence of this second magnetic ion on the spin correlations and spin dynamics was checked in comparison with $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$ where Y is non magnetic. The amount of hydrogen (or deuterium) introduced ($y=1$ or $y=4$) allows to vary interatomic distances in a large range. In this range, the $d_{\text{Mn-Mn}}$ distance (2.77 Å for $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_1$, and 2.87 Å for $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$) remains above the magnetic instability threshold for the Mn moments ($d_0 \simeq 2.66$ Å).

In comparison with the disordered compounds we studied the spin fluctuations in ordered TbMn_2D_4 , TbMn_2H_4 , and YMn_2H_4 . Their simple long range antiferromagnetic structure, which is determined by the H superstructure^{7,8}, is a reference to check the influence of hydrogen or deuterium disorder on the spin fluctuations.

III. NEUTRON DIFFRACTION MEASUREMENTS

We studied the magnetic correlations on the powder diffractometer G6-1 of the reactor Orphée (with an incident neutron wavelength of 4.734 Å). Temperature varied between 350 K and 10 K. A spectrum measured in the paramagnetic range was subtracted to extract the magnetic correlations. The magnetic spectra of the Al substituted samples show diffuse magnetic peaks, corresponding to short range antiferromagnetic correlations (Fig. 1). The peak positions are indexed with the same

propagation vector as in the ordered parent compound RMn_2D_4 . Using the Fullprof program¹⁶, we refined the data assuming short range ordered antiferromagnetic regions of diameter L_c with ordered moments μ_R and μ_{Mn} , keeping the same type of order as in Ref. 8. Results are given in Table I. We find correlated regions of extension L_c between 15 and 30 Å. L_c is temperature independent, but varies with H content and R substitution. The presence of magnetic Tb ions increases L_c with respect to non magnetic Y. It also induces *ferromagnetic* correlations on a shorter length scale (about 6 Å). These ferromagnetic correlations, shown by an increase of the magnetic scattering at low angles coexist with the antiferromagnetic ones. The short range ordered moments remain well below the moments in the long range ordered samples ($\mu_{\text{Mn}}=4 \mu_B$ and $\mu_{\text{Tb}}=9 \mu_B$ in ordered TbMn_2D_4 for instance). In spite of the strong magnetic disorder, the transition temperatures T_{SRO} towards the short range ordered state are in the range 100-250 K, therefore not much decreased with respect to the Néel temperature of the long range ordered state ($T_N=300$ K in TbMn_2D_4 and 330 K in YMn_2D_4). This was also the case of other disordered hydrides previously studied¹². A detailed description of the short range magnetic order in the $\text{R}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{H}_y$ family will be given later.

IV. MAGNETIC MEASUREMENTS

The magnetization was measured with a SQUID magnetometer, under static magnetic field of 10 Oe, in the zero field cooling (zfc) and field cooling (fc) conditions. Typical curves are shown in Fig. 2. In all disordered samples, magnetic irreversibilities start around 230-280 K, namely above T_{SRO} . In the Y-samples, where only Mn sublattice is magnetic, the fc curve continuously increases with decreasing temperature, well above the zfc curve, which shows a broad maximum then flattens or decreases. The magnetization of the two Y-samples have the same order of magnitude in the paramagnetic regime, but in the irreversibility region, the magnetization is much smaller for the sample with low hydrogen content. The temperature dependence of both fc and zfc curves is reminiscent of the behavior in cluster glasses¹⁷⁻¹⁹, where magnetic order occurs within spatially limited regions, and the relative orientations of the superparamagnetic-like spin clusters depend on the cluster interaction field, anisotropy field, and thermal activation²⁰. In the Tb-samples with two magnetic sublattices, this cluster glass behavior is superimposed on a global paramagnetic component, with a variation close to $1/T$. This second component should be related with the strong thermal fluctuations of the Tb moments, which become progressively polarized by the Tb-Mn exchange field as temperature decreases⁸. In all the short range ordered samples, anomalies are observed in the low temperature range (30-50 K), as shown by a small maximum in the zfc curve,

and an upturn of the fc curve. Similar anomalies were predicted and observed in some cluster glasses, when the local anisotropy fields start to be significant²⁰. They suggest the presence of small superparamagnetic clusters which could fluctuate down to low temperatures, having their anisotropy fields perpendicular to the interaction fields²⁰. In $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$, the low temperature anomalies result in a plateau on the fc curve. This plateau, whose origin is unexplained, reaches only about 3 % of the maximum expected due to demagnetization effect.

In comparison with the short range ordered compounds, the magnetization of YMn_2D_4 and TbMn_2D_4 with long range antiferromagnetic order is shown in the insets. In both samples, the magnetic irreversibilities start abruptly at the Néel temperature T_N measured by neutrons^{7,8}. In YMn_2D_4 , a magnetization plateau is observed below T_N , with a value of about 3 % of the demagnetization value. This plateau, rather unusual for an antiferromagnet, is presumably connected with the first order character of the transition, yielding a spin blocking induced by hydrogen order and ordered antiferromagnetic moment which remains close to saturation almost up to T_N . TbMn_2D_4 shows a similar behavior, with an additional paramagnetic component. In both samples, the low temperature anomalies observed in the short range ordered samples are absent.

V. INELASTIC NEUTRON SCATTERING

A. experimental set up and data analysis

The experiments were performed in the time of flight spectrometer Mibemol of the reactor Orphée, with an incident wavelength of 5 Å (incident energy of 3.27 meV). The energy resolution (FWHM=0.15 meV) and the efficiency of the detectors were determined by measuring a vanadium standard of the same plate-like shape as the samples. After background and absorption corrections, the neutron cross sections were calibrated in absolute scale using the vanadium spectrum. Measurements were performed *versus* temperature, using either a closed cycle nitrogen flow cryo-oven (between 350 K and 100 K) or a helium flow cryostat (between 300 K and 20 K). The maximum temperature of 350 K was chosen to avoid any decomposition of the samples due to hydrogen migration. The temperature range allowed us to study the spin fluctuations in the paramagnetic range, and to follow their evolution below the transition. The range of the elastic scattering vector is the same as in the diffraction measurements.

The scattering cross section for magnetic quasielastic neutron scattering can be expressed in a general form

$$S(q, \omega) = \frac{1}{\pi} n(\omega) \chi_q''(\omega) \quad (1)$$

where $n(\omega)$ is the Bose factor taking into account the thermal population factor of the fluctuations, and $\chi_q''(\omega)$ the dynamical susceptibility yielding the response of the system. Within linear response theory, $\chi_q''(\omega)$ is the product of the static transverse susceptibility $\chi(q, \omega=0)$, and the spectral function $F(\omega)$. In the simplest case of a single exponential decay (SED), there is a single energy Γ (or equivalently a single relaxation rate $\tau=1/2\pi\Gamma$, taking $\hbar=1$) for the magnetic fluctuations, so that the spectral function is expressed as $F(\omega) = \frac{1}{\pi} \frac{\Gamma}{\Gamma^2 + \omega^2}$. In classical spin glasses like CuMn, the spectral response was expressed by a distribution of Lorentzians corresponding to a distribution of relaxation rates^{23,24}. Still, the quasielastic scattering cross section in the experimental energy range was well fitted by a single Lorentzian lineshape²³.

This simple model could not account for our data, yielding strong misfits even in the paramagnetic range. Therefore we considered explicitly an energy distribution in the spectral lineshape. We took two limiting forms for this distribution, namely a bimodal distribution (model 1) and a uniform distribution (model 2). Model 1 assumes two typical energies Γ_1 and Γ_2 ($\Gamma_1 < \Gamma_2$) for the spin fluctuations. It was used previously to analyze the spin dynamics in cluster glasses^{21,22}. Model 2 assumes that the energies of the spin fluctuations are distributed with an equal probability between lower and higher energy bounds Γ_1 and Γ_2 . It was recently proposed by Bernhoeft²⁵ within a general model of the dynamical phase inhomogeneities in non Fermi liquid systems.

The quasielastic neutron cross section is written - within model 1:

$$S(q, \omega) = \frac{\omega}{e^{\omega/kT} - 1} (F_1(\omega) \chi_1(q) + F_2(\omega) \chi_2(q)) \quad (2)$$

where χ_1 and χ_2 are the static susceptibilities of the two quasielastic contributions and the spectral functions are respectively

$$F_1(\omega) = \frac{1}{\pi} \frac{\Gamma_1}{\Gamma_1^2 + \omega^2} \quad F_2(\omega) = \frac{1}{\pi} \frac{\Gamma_2}{\Gamma_2^2 + \omega^2} \quad (3)$$

with Γ_1, Γ_2 being the corresponding energy linewidths. The static susceptibility is defined as $\chi = \chi_1 + \chi_2$.

- within model 2:

$$S(q, \omega) = \frac{\omega}{e^{\omega/kT} - 1} F(\omega) \chi(q) \quad (4)$$

where χ is the static susceptibility and $F(\omega)$ the spectral function written as

$$F(\omega) = \frac{1}{\pi} \frac{1}{\ln(\Gamma_2) - \ln(\Gamma_1)} \frac{1}{\omega} \left(\arctan\left(\frac{\omega}{\Gamma_1}\right) - \arctan\left(\frac{\omega}{\Gamma_2}\right) \right) \quad (5)$$

where Γ_1 and Γ_2 are respectively the low and high energy limits of the energy distribution.

In the above expressions, $\omega > 0$ corresponds to a neutron energy gain. The prefactors in equations (3) and

(5) normalize to unity the energy integration of the spectral function. Therefore, in the high temperature limit $\omega \ll kT$ (valid here in the paramagnetic range and down to about 50 K), the quantity $T\chi$ is equal to the energy-integrated intensity of the quasielastic signal. The fitted energy widths do not depend on the normalisation factor.

In the limit of a Curie-Weiss behavior, the neutron susceptibility is related to the effective fluctuating moment by the expression: $\chi(q=0, T) = A \frac{m_{eff}^2 \mu_B^2}{3kT}$. A corresponds to the calibration of the neutron cross section in absolute scale. This expression provides an effective moment value, to be compared with the value from bulk magnetic measurement.

The total cross section is written as

$$S^{\text{total}}(q, \omega) = c_{el}\delta(\omega) + S(q, \omega) \quad (6)$$

The neutron intensity I detected *versus* time of flight t at the scattering angle 2θ is proportional to the quantity:

$$I(\theta, t) \propto \frac{1}{t^4} S^{\text{total}}(q, \omega) \quad (7)$$

The neutron intensity was convoluted with the experimental resolution and fitted to each individual time of flight (TOF) spectrum, with c_{el} (intensity of the elastic peak), Γ_1 , Γ_2 , and χ_1 , χ_2 (model 1) or χ (model 2) as parameters. A very small linear background was also added in the fit. The fit was performed in the energy range (-20, 2) meV, where the phonon contribution is small and could be neglected.

B. results

a) short range ordered samples

We first show the results in $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_y$ ($y=1$ and $y=4$). In spite of their different D contents, ordering temperatures and magnetic correlations lengths, the behavior of the magnetic fluctuations is the same for the two samples. Typical TOF spectra are shown in Figs. 3 and 4 for temperatures respectively above and below T_{SRO} . Note that due to the t^{-4} factor of equation (7), the maxima of the quasielastic signals are shifted with respect to the elastic one. In spite of this distortion, the time dependent plot were preferred to the energy dependent ones (in inset), since they provide a better estimation of the fit quality at low energies.

Whatever the model chosen for the spectral function, the general evolution with temperature can be described as follows. Above T_{SRO} , the susceptibility follows a Curie law, and the quasielastic integrated intensity $T\chi$ is temperature independent (Fig. 5). Below T_{SRO} , we observe a gradual transfer of intensity from the quasielastic signal to the elastic one, the sum of the two contributions being conserved with temperature. The high energy signal of width Γ_2 dominates, with a weight of 80% of the susceptibility at high temperature. The energy linewidths

have a rather original behavior (Fig. 6). Above T_{SRO} , Γ_1 and Γ_2 are temperature independent. Below T_{SRO} , the small linewidth Γ_1 starts to decrease whereas the large linewidth Γ_2 *increases* with decreasing temperature. This behavior is the same for all q values. In the paramagnetic regime, the quasielastic cross section is well fitted by the two models. Below T_{SRO} , model 1 still yields very good fit of the data, whereas model 2 starts to show some misfits. They occur mainly below 80 K where the linewidths Γ_1 and Γ_2 are very different. We have therefore restricted the use of model 2 to temperatures above 80 K, where this model was meaningful. In the paramagnetic range, the two models give an energy linewidth in the same energy range, with Γ_1 around 0.1 meV, and Γ_2 around 3-5 meV.

The q dependence of the susceptibility and quasielastic widths is shown in Fig. 7. The susceptibility χ shows a weak and broad modulation with respect to the form factor of the free ion. This modulation remains the same below T_{SRO} . The magnetic correlations observed below T_{SRO} by neutron diffraction correspond to a modulation of the *elastic* component. The energy linewidths are almost q -independent, both above and below T_{SRO} . The $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_1$ sample, where the magnetic correlations are enhanced, shows the same behavior.

In $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$, the magnetic signal coming from Mn ions only is much smaller, but still shows the complex lineshape described above. The main difference with the Tb samples concerns the temperature dependence of the large energy linewidth Γ_2 , which now strongly *decreases* below T_{SRO} (Fig. 8). This is observed whatever the model used to describe the spectral function.

b) long range ordered samples

In comparison, we show the magnetic fluctuations in TbMn_2D_4 , TbMn_2H_4 , and YMn_2H_4 where long range magnetic order occurs at T_N through a first order magnetocrystallographic transition. Above T_N , the magnetic fluctuations are very similar in the ordered and in the disordered samples. The main effect of the LRO is a strong suppression of the quasielastic intensity below T_N . For example, at $T = T_N/2$ the intensity of the magnetic fluctuations is decreased by a factor 3 with respect to its value in the paramagnetic state in the ordered Tb samples, and by a factor 5 in ordered YMn_2H_4 , whereas it decreases by 30% in disordered $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_1$ and only 8% in $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$. The second important difference is the occurrence of a well defined localized excitation in the ordered Tb samples below T_N .

In Fig. 9, we show two typical TOF spectra for TbMn_2D_4 at 340 K and 160 K, namely above and below T_N . At 340 K, the spectral lineshape is well fitted by a bimodal distribution (model 1), with typical energy widths of 0.5 and 2 meV, therefore comparable to the energy widths of the disordered samples at the same temperature. Below T_N , a purely inelastic signal appears in the TOF spectra, coexisting with the quasielastic one. This new component was fitted by a Gaussian lineshape, of

energy E_0 and width Γ_{inel} . Its intensity (fig. 10a) shows a broad maximum versus temperature. The energy E_0 slightly increases from 6 to 7 meV when temperature decreases (Fig 10b), with constant energy width Γ_{inel} of 2 meV. The quasielastic signal strongly decreases just below T_N , but still persist in the ordered state. The large energy width Γ_2 increases with decreasing T , whereas the small energy width Γ_1 is about temperature independent. The sum of the three contributions (elastic, quasielastic and inelastic) is conserved with temperature.

In TbMn_2H_4 , the inelastic and quasielastic signals are the same as in the TbMn_2D_4 . The elastic component is enhanced by about a factor 10 in TbMn_2H_4 , due to the large incoherent contribution of the hydrogen isotope. As expected from previous inelastic neutron studies of Laves hydrides²⁶, the dynamics of hydrogen ordering cannot be resolved in the present experiment. In other words, hydrogen (or deuterium) is frozen at the time scale of the neutron experiment ($t=9\times 10^{-12}\text{s}$), and there is no interference between H or D diffusion and the magnetic fluctuations.

Finally, in ordered YMn_2H_4 (Fig 11), the quasielastic signal above T_N also consists of two components. Below T_N , it becomes very small but can still be detected down to 100 K. The energy width in the paramagnetic state are about the same as in the disordered $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$, but here they do not vary much with temperature. The inelastic localized mode observed in the ordered Tb samples was not observed.

VI. DISCUSSION

A. paramagnetic regime

In the high temperature range where the samples show a Curie-Weiss behavior, the effective moments deduced from the integration of the quasielastic neutron cross section agree with the value deduced from magnetization (table II). This means that most of the spin fluctuations are probed by the experimental time window, and rules out the presence of high energy spin fluctuations (in the 50 meV range or above), similar to that observed in YMn_2 ^{27,28}, $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2$ ¹³ or other itinerant systems. Therefore, all samples are in the localized moment limit, even at low H(D) content, and the wide energy distribution seen in both Tb and Y samples should be connected with peculiar features of the magnetic disorder. At high temperature, for localized spins coupled by near neighbor interactions, the energy linewidth of the magnetic fluctuations is related to the values of the exchange constants²⁹. This is the case of the present samples, where the anisotropy energy is much smaller than the exchange energy³⁰. Within molecular approximation, the lineshape of the response function is expected to be intermediate between Gaussian and Lorentzian, and its

second moment, which measures the quasielastic width is given for a polycrystalline sample by

$$\overline{\omega^2} = (8/3)S(S+1) \sum_i J^2(R_i)(1 - \sin(qR_i)/(qR_i)) \quad (8)$$

In this model, the energy linewidth $\sqrt{\overline{\omega^2}}$ is temperature independent, in agreement with experiment, and in contrast with the behavior of itinerant systems where the linewidth increases linearly with temperature (Korringa behavior). Assuming first neighbor interactions only ($R_1=2.86 \text{ \AA}$), the smooth variation of the linewidth predicted by equation (8) above $1 \text{ \AA}^{-1}$ is also consistent with experiment (Fig. 7b), although the expected decrease at low q values is not seen.

The distribution of linewidths may be connected with a distribution of exchange constants, induced by the frozen hydrogen or deuterium disorder. As discussed previously for the ordered compounds YMn_2D_4 , the presence of a H(D) atom near a Mn-Mn pair modifies the amplitude, and even the sign, of the first neighbor exchange interaction⁸. The various environments of the Mn atoms having zero or one H(D) atom nearby the Mn pairs should be at the origin of the linewidth distribution. In the Tb samples, the magnetic fluctuations are dominated by the Tb moments of much larger magnitude. The distribution of linewidths therefore mostly measures the distribution of Tb-Mn interactions, showing that they are also sensitive to the number of H(D) near neighbors atoms. This is also consistent with the analysis of the ordered structure⁸. Taking $S_{\text{Mn}}=2$, and summing equation (8) over the 6 first neighbors of a Mn ion, we obtain from the two energy widths in $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$, low and high limits for the Mn-Mn exchange constant $\sqrt{J^2_{\text{Mn-Mn}}}$ equal to 0.03 and 0.3 meV. A similar evaluation for $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$ ($S_{\text{Tb}}=3$) yields limit values for the the Tb-Mn exchange constant $\sqrt{J^2_{\text{Tb-Mn}}}$ equal to 0.03 and 0.1 meV.

B. ordering transition

In the long range ordered compounds, the transition is of first order, whereas in the short range ordered compounds, it is close to second order^{7,11}. As shown previously, H(D) order is the key parameter which controls the frustration. In the LRO samples, the first order transition is directly connected with the formation of H(D) superstructure which relieves the frustration of the Mn lattice. In contrast, in the disordered samples, the second order transition occurs in a range of temperature where the slowing down the H(D) diffusion yields a more progressive change from thermal to frozen disorder. In both cases, the present results show that the transition is characterized by a deep change in the magnetic fluctuations, namely, i) a transfer of intensity from the quasielastic to

elastic signal connected with the onset of *static* correlations, and ii) a change in the behavior of the quasielastic widths, which start to vary with temperature.

The transition temperature T_{SRO} remains in the range 100-250 K, therefore is not much decreased with respect to the Néel temperature of the ordered compounds (300-330 K). Such high transition temperature is often observed in cluster glasses³¹. It contrasts with classical spin glasses where the spin glass temperature is typically ten times smaller than the transition temperature of the ordered parent compound³¹⁻³³. The average exchange constant $J_{\text{Mn-Mn}}$ deduced from T_N in the mean field approximation ($T_N = \sum_i \frac{2}{3} J_{\text{Mn-Mn}} S_{\text{Mn}} (S_{\text{Mn}} + 1)$, summing over the 6 first neighbors of a Mn ion) yields $J_{\text{Mn-Mn}} = 0.9$ meV, which is about 3 times higher than the upper limit for $\sqrt{J^2_{\text{Mn-Mn}}}$ deduced from the linewidths in the paramagnetic regime. Obviously, such evaluations only provide an order of magnitude of the exchange constant since they neglect the influence of inhomogeneity and frustration.

A simple picture in terms of a cluster glass can account for the observed decrease of T_N with respect to the ordered state. One assumes clusters of diameter L_c (where L_c is the correlation length) consisting of an ordered core surrounded by a disordered layer of thickness d (where $d = 2.8\text{\AA}$ is the first neighbor distance). In first approximation, the decrease of T_N is given by the percentage disordered spins, assuming that they do not contribute to the average exchange interaction. For the Tb samples ($T_N = 300\text{K}$ in ordered TbMn_2D_4), this simple picture yields short range ordering temperatures of 112K ($y=4$) and 161K ($y=1$), in relatively good agreement with the experimental values (135K and 200K respectively). A better evaluation would require to define different inter and intracenter exchange interactions, as proposed in mean fields models of cluster glasses³⁴.

The coexistence of highly frustrated and low frustrated spins yields a large distribution of energy barriers, as observed in cluster glasses or inhomogeneous superparamagnets. The magnetization data support this qualitative picture, showing that some spins could freeze either above T_{SRO} (up to the Néel temperature of the ordered compound), or well below T_{SRO} down to the low T range.

C. spin dynamics below the transition

As temperature decreases, more and more spins freeze and contribute to the static clusters. The fluctuating spins remain almost uncorrelated like in the paramagnetic regime. In $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$, the decrease of the two quasielastic widths suggests that these uncorrelated spins relax between several metastable configurations, with typical times ($\tau = 1/2\pi\Gamma$) increasing with decreasing temperature.

In the Tb samples, the formation of the static clusters is associated with the emergence of two types of spin dy-

namics : a relaxation process involving weakly coupled and almost uncorrelated spins, as shown by the decrease of the small quasielastic width Γ_1 , and an excitation process as shown by the increase of the large quasielastic width Γ_2 . Here the magnetic signal is dominated by the Tb spins. In ordered TbMn_2D_4 , a local mode of energy E_0 is clearly observed below T_N , and is attributed to local fluctuations of the Tb spins in the static Mn molecular field. Such mode is predicted and observed in ordered RFe_2 or RAl_2 Laves phases^{35,36}. Its energy is expected to increase smoothly with temperature like the ordered Mn moment ($E_0 \propto J_{\text{Tb-Mn}} S_{\text{Mn}}$). In the short range ordered Tb compounds, one should also expect a similar inelastic mode, but broadened by the distribution of exchange interactions and situated at a lower energy, due to the lower value of the short range ordered Mn moment. Therefore, this mode could be hidden by the large quasielastic signal. In order to check this assumption, we have performed for $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$ the same fit as for ordered TbMn_2D_4 . It yields a slight improvement of the fit quality, with an inelastic contribution of about 10% of the quasielastic one. The energy E_0 is smaller than in TbMn_2D_4 and increases more rapidly with decreasing temperature (from 3 to 5 meV), as expected from a simple model. The quasielastic widths, especially the low energy width Γ_1 are not much affected.

This analysis points out the strong similarities between the spin fluctuations in the short range and long range ordered Tb compounds. It also suggests that the large quasielastic signal and the inelastic one have the same nature, and we note that their characteristic energies E_0 and Γ_2 vary in the same way with temperature. The onset of short range order weakens the energy of the inelastic mode, and changes the balance between the two contributions. The persistence of a quasielastic signal in the ordered state, which is not observed in RFe_2 Laves phases, is presumably related to the influence of hydrogen or deuterium. The lowering of symmetry due to the H(D) superstructure⁸ might create lower energy levels which cannot be distinguished from the quasielastic scattering. The residual disorder, since one H(D) site is halfly occupied, could also play a role. Whatever the exact mechanism, we have observed local excitations of low energy which develop as soon as a static magnetic order freezes in, and are almost insensitive to the correlation length. A better analysis of these excitations would require higher resolution measurements on a single crystal.

VII. CONCLUSION

In the Laves compounds $\text{R}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_y$ with deuterium or hydrogen disorder, a transition towards short range magnetic order is probed by neutron scattering. It is shown by the occurrence of static clusters of a few tens of Angstroms, with a size independent of temperature. The transition temperature T_{SRO} is high in spite of the

small cluster size, and the transition is close to second order, in contrast with the first order transition in the long range ordered compounds. In the paramagnetic range, the complex lineshape of the spectral function suggests a distribution of exchange constants, possibly related to the onset of nonequivalent magnetic bonds and the influence of frozen H(D) configurations. Below T_{SRO} , several types of fluctuations are observed, depending on the presence of the Tb magnetic ion. They are attributed either to the relaxation of almost uncorrelated spins, or to local spin excitations within the frozen clusters. The spin fluctuations in the short range and long range ordered compounds show strong similarities. The overall behavior and the macroscopic magnetic properties are interpreted in terms of a cluster glass, where short range ordered regions with local H(D) order and low frustration coexist with strongly frustrated and uncorrelated spins. It would be interesting to know if the observed spin fluctuations arise from the peculiar coupling of hydrogen and magnetic lattices, or if they could be observed in other cluster glasses or disordered magnets with topological frustration.

ACKNOWLEDGMENTS

We thank N. Bernhoeft, M. Hennion, P.A. Alekseev and J.C. Gómez Sal for many interesting discussions. P. C.-P. is supported by Fundação para a Ciência e a Tecnologia, Portugal, through the research grant PRAXIS XXI/BD/20334/99. This work was partly supported by the Russian foundation for Basic Research, Grant N. 02-02-06085, and the Russian State Program 'Neutron Investigations of Condensed Matter'.

¹ S. Sachdev Quantum Phase Transitions, *Cambridge University Press* (1999).

² R. Ballou, J. Deportes, R. Lemaire, Y. Nakamura, B. Ouladiaz, J. Magn. Magn. Mater. **70**, 129 (1987).

³ M. Shiga, Physica B **149**, 293 (1988).

⁴ C. Ritter, S. H. Kilcoyne, R. Cywinski, J. Phys.: Condens. Matter **3**, 727 (1991).

⁵ I. Mirebeau, I.N. Goncharenko, I. V. Golosovsky, Phys. Rev. B, **64**, 140401(R) (2001).

⁶ P. Vajda, *Handbook on the Physics and Chemistry of Rare Earths vol.20*, Elsevier, Amsterdam (1995).

⁷ I. N. Goncharenko, I. Mirebeau, A. V. Irodova, E. Suard, Phys. Rev. B **56**, 2580 (1997).

⁸ I. N. Goncharenko, I. Mirebeau, A. V. Irodova, E. Suard, Phys. Rev. B **59**, 9324 (1999).

⁹ H. Figiel, J. Przewoznik, V. Paul-Boncour, A. Lindbaum, E. Gratz, M. Latroche, M. Escorne, A. Percheron-Guégan, P. Mienowski, J. Alloys Compds. **274**, 29 (1998).

¹⁰ M. Latroche, V. Paul-Boncour, A. Percheron-Guégan, F. Bourée-Vigner, G. André, J. Solid State Chem. **154**, 398 (2000).

¹¹ I. Mirebeau, I. N. Goncharenko, D. Andreani, E. Suard, Phys. Rev. B **62**, 9493 (2000).

¹² P. Cadavez-Peres, I. N. Goncharenko, I. Mirebeau, R. Gladkikh, O. L. Makarova, Appl. Phys. A, **74**, S692, (2002)

¹³ K. Motoya, S. M. Shapiro, L. Rebersky, M. S. Torikachvili, Phys. Rev. B **44**, 183 (1991).

¹⁴ H. Nakamura, Y. Yoshimoto, M. Shiga, M. Nishi, K. Kakurai, J. Phys.: Condens. Matter **9**, 4701 (1997).

¹⁵ R. Ballou, E. Lelièvre-Berna, B. Fåk, Phys. Rev. Lett. **76**, 2125 (1996).

¹⁶ J. Rodríguez-Carvajal, Physica B **192**, 55 (1993).

¹⁷ M. Koyano, M. Suezawa, H. Watanabe, M. Inoue, J. Phys. Soc. Jpn. **63**, 1114 (1994).

¹⁸ D. A. Pejakovic, J. L. Manson, J. S. Miller, A. J. Epstein, Phys. Rev. Lett. **85**, 1994 (2000).

¹⁹ J. C. Gómez Sal, J. I. Espeso, J. Rodríguez Fernández, N. Marcano, J. A. Blanco, J. Magn. Magn. Mater. **242-245**, 125, (2002).

²⁰ P. Nozar, V. Sechovsky, V. Kambarsky, J. Magn. Magn. Mater. **69**, 71 (1987).

²¹ H. Scheuer, M. Lowenhaupt, W. Just, J. Magn. Magn. Mater. **4**, 77 (1977).

²² I. Mirebeau, G. Iancu, M. Hennion, G. Gavoille, J. Hubsch, Phys. Rev. B **54**, 15928 (1996).

²³ A. P. Murani, J. de Physique, Colloque C6 **39**, 1517 (1978).

²⁴ A. P. Murani, J. Phys. F, **15**, 417, (1985).

²⁵ N. Bernhoeft, J. Phys.: Condens. Matter **13**, R771 (2001).

²⁶ S. I. Campbell, M. Kemali, D. K. Ross, Physica B **241-243**, 326 (1998).

²⁷ J. Deportes, B. Ouladiaz, K. R. A. Ziebeck, J. Magn. Magn. Mater. **70**, 14 (1987).

²⁸ T. Freltoft, P. Böni, G. Shirane, K. Motoya, Phys. Rev. B **37**, 3454 (1988).

²⁹ W. Marshall, S. W. Lovesey, *Theory of Thermal Neutron Scattering*, University Press, Oxford (1971).

³⁰ P. Cadavez-Peres, I. N. Goncharenko, I. Mirebeau, Phys. Rev. B **64**, 94419 (2001).

³¹ M. Itoh, I. Natori, S. Kubota, K. Motoya, J. Phys. Soc. Jpn. **63**, 1486 (1994).

³² M. Shiga, T. Satake, H. Wada, Y. Nakamura, J. Magn. Magn. Mater. **51**, 123 (1985).

³³ A. Z. Menshikov, G. P. Ganiskova, J. Phys.: Condens. Matter **6**, 791 (1994).

³⁴ C. M. Soukoulis, K. Levin, Phys. Rev. B **18**, 1439 (1978).

³⁵ L. Paolasini, PhD thesis, Université Joseph Fourier-Grenoble I, Grenoble, France (1996).

³⁶ J. J. Rhyne, N. C. Koon, J. Appl. Phys. **49**, 2133 (1978).

Figure captions

Fig.1: Magnetic neutron diffraction spectra at 10 K for $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_y$ ($y=4$ and $y=1$) and $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$, measured on G6-1 diffractometer ($\lambda=4.734$ Å). A spectrum measured in the paramagnetic range was subtracted to extract the magnetic contribution. For $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$, the first antiferromagnetic

peak is not observed since magnetic moments are along direction $\langle 111 \rangle$. Solid lines are fits of the data, yielding the short range ordered magnetic moments and correlations lengths given in Table 1.

Fig.2: Low field magnetization in $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})\text{D}_y$ ($y=4$ and $y=1$), and in $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})\text{D}_y$ ($y=4$ and $y=1$), measured in a static field $H=10$ Oe, using zero field cooling (zfc) and field cooling (fc) conditions. Insets: low field magnetization of the long range ordered YMn_2D_4 and TbMn_2D_4 compounds. The transition temperature T_{SRO} towards short range order is shown by arrows. Other arrows point out the low temperature anomalies.

Fig.3:

Time of flight (TOF) spectrum of $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})\text{D}_4$ at 250 K (paramagnetic range), focusing on the quasielastic region. Spectra were regrouped for detectors within an angular range 23.5–63.1 degrees. Fits with model 1 (a) and model 2 (b) are shown by solid lines. Inset: the corresponding neutron cross section *versus* energy transfer, and a schematic drawing of the distribution of energy widths for each model.

Fig.4: TOF spectrum of $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})\text{D}_4$ at 80 K (below T_{SRO}), in an angular range 23.5–63.1 degrees. Fits with model 1 (a) and model 2 (b) are shown by solid lines. Inset: the corresponding neutron cross section *versus* energy transfer and a schematic drawing of the distribution of energy widths for each model.

Fig.5: Elastic, quasielastic intensity $T\chi$, and sum of the two contributions *versus* temperature in $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$. TOF spectra have been regrouped within an angular range 23.5–63.1 degrees. Models 1 and 2 give equivalent results.

Fig.6: Quasielastic widths Γ_1 and Γ_2 *versus* temperature in $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$, obtained by fitting the data with model 1 (a) and model 2 (b).

Fig.7: Results obtained in $\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$ with model 1. a) Quasielastic intensity *versus* q for two temperatures, 200 K and 80 K, above and below T_{SRO} respectively. Solid lines correspond to the squared magnetic form factors of Tb and Mn ions. Dotted lines are guides to the eye. b) Quasielastic widths Γ_1 and Γ_2 *versus* q at 200 K. Solid lines are fits with the equation (8) described in text. c) Quasielastic widths *versus* q at 80 K.

Fig.8: Quasielastic widths Γ_1 and Γ_2 *versus* temperature in $\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$, obtained with model 1.

Fig.9: TbMn_2D_4 : TOF spectra at 340 K and 160 K, ($T_{\text{N}}=300$ K). In inset, the corresponding neutron cross section *versus* energy transfer. Solid lines are fits with model 1, adding an inelastic contribution below T_{N} .

Fig.10: TbMn_2D_4 : a) variation of the integrated intensities *versus* temperature, b) quasielastic widths Γ_1 and Γ_2 and energy E_0 of the inelastic signal *versus* temperature.

Fig.11: YMn_2H_4 : a) variation of the integrated intensities *versus* temperature, b) quasielastic widths Γ_1 and Γ_2 *versus* temperature.

Table captions

R	y (exact value)	T_{SRO} (K)	L_c (Å)	μ_{Mn} (μ_B)	μ_{R} (μ_B)
Tb	4 (3.87)	135 (10)	20 (2)	1.7 (3)	3.5 (5)
Tb	1 (1.04)	200 (10)	30 (3)	2.5 (3)	8.8 (8)
Y	4 (3.81)	250 (10)	13 (2)	1.8 (2)	–
Y	1 (1.38)	190 (10)	15 (3)	3.0 (3)	–

TABLE I. Transition temperature T_{SRO} , correlation length L_c and short range ordered magnetic moments at low temperature (8-11 K) deduced from neutron diffraction data in the $\text{R}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_y$ samples. Error bars are mentioned in units of the last digit.

Compound	Effective magnetic moment (μ_B)	
	(Magnetization)	(Neutron scattering)
$\text{Y}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$	4.1 ± 0.2	4.0 ± 0.6
$\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_4$	10.1 ± 0.5	11.9 ± 1.8
$\text{Tb}(\text{Mn}_{0.9}\text{Al}_{0.1})_2\text{D}_1$	10.2 ± 0.5	11.6 ± 1.7

TABLE II. Effective magnetic moments per chemical formula in the paramagnetic regime, deduced from magnetic and inelastic neutron scattering measurements.